



## Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Kristina Brew  
4453 Larkin Crossroad  
Armstrong, BC V0E 1B6 CA

Date: 27-Aug-20  
Shear ID: 203155  
Test No: 200730


### Animal and Sample Description

Animal Name: BAL TAHIR  
Registry #: 32110241  
Breed: Huacaya  
Sex: Male  
Colour: 301 - Medium Brown

Date of Birth (Age): 10-Jun-12  
Sample Location: GRID  
Sample Date: 25-Apr-20  
Previous Shear Date: 4-May-19  
Total Fleece Wt (lbs): 9.80

### Laboratory Data

Mean Fiber Diameter:	23.1 microns	Mean Staple Length:	92 mm
Standard Deviation:	6.1 microns	Length Standard Deviation:	3.7 mm
Coefficient of Variation:	26.4 %	Length Coefficient of Variation:	4.0 %
Spin Fineness:	23.6 microns	Mean Curvature:	31.9 deg/mm
Fibers Greater Than 30 microns:	10.9 %	SD Curvature:	19.5 deg/mm
Comfort Factor:	89.1 %	Medullated Fibers:	%



### Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear  
Business Manager

Jude Davidson  
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: [nz.wool.timaru@sgs.com](mailto:nz.wool.timaru@sgs.com) Web: [www.wooltesting.sgs.com](http://www.wooltesting.sgs.com)