



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Kristina Brew
4453 Larkin Cross Road, V0E 1B6
Armstrong, BC, Canada

Date: 26-May-22
Shear ID: 231122
Test No: 606253


Animal and Sample Description

Animal Name: Brycarda's Ares
Registry #: 36042906
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 27-Jun-20
Sample Location: GRID
Sample Date: 30-Apr-22
Previous Shear Date: 1-May-21
Total Fleece Wt (lbs): 6.1

Laboratory Data

Mean Fiber Diameter:	16.5 microns	Mean Staple Length:	105 mm
Standard Deviation:	3.4 microns	Length Standard Deviation:	7.7 mm
Coefficient of Variation:	20.6 %	Length Coefficient of Variation:	7.3 %
Spin Fineness:	16.0 microns	Mean Curvature:	52.2 deg/mm
Fibers Greater Than 30 microns:	0.2 %	SD Curvature:	20.8 deg/mm
Comfort Factor:	99.8 %	Medullated Fibers:	1.7 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com