



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Kristina Brew
4453 Larkin Cross Road, V0E 1B6
Armstrong, BC, Canada

Date: 26-May-22
Shear ID: 231119
Test No: 606250


Animal and Sample Description

Animal Name: Bourbon's Cognac
Registry #: 36042975
Breed: Huacaya
Sex: Male
Colour: 202 - Light Fawn

Date of Birth (Age): 27-May-21
Sample Location: GRID
Sample Date: 30-Apr-22
Previous Shear Date:
Total Fleece Wt (lbs): 7.9

Laboratory Data

Mean Fiber Diameter:	19.9 microns	Mean Staple Length:	112 mm
Standard Deviation:	4.4 microns	Length Standard Deviation:	1.1 mm
Coefficient of Variation:	22.3 %	Length Coefficient of Variation:	1.0 %
Spin Fineness:	19.6 microns	Mean Curvature:	41.6 deg/mm
Fibers Greater Than 30 microns:	2.4 %	SD Curvature:	17.1 deg/mm
Comfort Factor:	97.6 %	Medullated Fibers:	6.4 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com