



Optical Fiber Diameter Analyser (OFDA100) Micron Test Report

Kristina Brew
4453 Larkin Cross Road, V0E 1B6
Armstrong, BC, Canada

Date: 26-May-22
Shear ID: 231118
Test No: 606249


Animal and Sample Description

Animal Name: Bourbon's Amaretto of Brycarda
Registry #: 36042838
Breed: Huacaya
Sex: Male
Colour: 100 - White

Date of Birth (Age): 11-Jul-21
Sample Location: GRID
Sample Date: 30-Apr-22
Previous Shear Date:
Total Fleece Wt (lbs): 6.3

Laboratory Data

Mean Fiber Diameter:	16.8 microns	Mean Staple Length:	135 mm
Standard Deviation:	4.0 microns	Length Standard Deviation:	3.2 mm
Coefficient of Variation:	23.7 %	Length Coefficient of Variation:	2.4 %
Spin Fineness:	16.8 microns	Mean Curvature:	52.4 deg/mm
Fibers Greater Than 30 microns:	0.7 %	SD Curvature:	21.6 deg/mm
Comfort Factor:	99.3 %	Medullated Fibers:	4.6 %



Test Performed According to Method AS/NZS 4492.5:2000

Jeremy Wear
Business Manager

Ioasa Kosena
Authorised Signatory

[SGS General Terms and Conditions](#)

The validity of this document may be confirmed by contacting the address shown below

SGS NZ LTD - 48 Kemp Street, Kilbirnie 6022, Wellington, New Zealand. Tel: 64-4-387 8565 Email: WoolOnline@sgs.com Web: www.wooltesting.sgs.com